

RIGIDPLY RAFTERS AYC GLULAM BEAM SPECIFICATIONS

Part I - General

1.1 System Description

- A. Beams shall be timbers of glue laminated Alaskan Yellow Cedar (AYC) as manufactured by Rigidply Rafters, Inc., Richland, PA 17087.
- B. Beams shall be stamped with the American Institute for Timber Construction (AITC) product quality mark.

Quality Assurance

- A. Manufacturer Qualifications:
 - 1. Minimum of 10 years' experience in manufacturing glued laminated timbers.
 - 2. Quality control system in compliance with ANSI A190.1-2022, *Product Standard for Structural Glued Laminated Timber*.
- B. Installer Qualifications:
 - 1. Minimum of 3 years' experience in building construction.

References:

- A. ANSI A190.1-2022 — *Product Standard for Structural Glued Laminated Timber*.
- B. AITC 200-2024 — *Manufacturing Quality Control Systems Manual for Structural Glued Laminated Timber*.
- C. ANSI 117-2025 — *Standard Specification for Structural Glued Laminated Timber of Softwood Species*.
- D. Pacific Lumber Inspection Bureau (2024) *WCLB Standard Grading Rules for West Coast & Imported Softwood Lumber, No. 18*.
- E. ASTM D2559-12a (2018) — *Standard Specification for Adhesives for Bonded Structural Wood Products for Use Under Exterior Exposure Conditions*.
- F. 2025 AWWPA Book of Standards, American Wood Protection Association
- G. American Institute of Timber Construction: *Test Methods for Structural Glued Laminated Timber*.

Handling, Storage, and Installation

- A. Handle only with web belting type slings. Use cleats or blocking to protect corners at pickup points.
- B. Store all beams properly and adequately to protect from damage on jobsite.
- C. Protect beams from adverse conditions prior to installation. (i.e. moisture damage.)
- D. Where appearance is important, coat beams with waterproof sealer.
- E. Proper installation of beams is the responsibility of the installer. See Rigidply Rafters Inc. "Glue-Laminated Wood Timber Handling and Storage Instructions" and relevant AITC Publication for additional information.

Part II - Materials

2.1 Lumber - Lumber shall be of untreated AYC as specified by the designer

- A. Untreated AYC shall be kiln dried to 15% with maximum moisture content of 16% prior to manufacturing.

2.2 Adhesives

- A. The face joint adhesive shall be wet-use adhesive conforming to "ASTM D 2559."
- B. The end joint (finger joint) adhesive shall be a wet-use adhesive conforming to "ASTM 25593."

Part III - Manufacturing

3.1 Process

- A. All lumber shall be regraded and checked for moisture content by the manufacturer.
- B. The laminations shall be made to length by finger jointing the individual pieces together. These structural finger joints shall be radio frequency cured.
- C. The laminations shall be surfaced, glued, and then clamped. The clamp-up shall be maintained at room temperature at a minimum pressure of 100 PSI.
- D. The beams shall be surfaced after gluing on the narrow faces of the laminations. ¹
- E. The corners exposed to view shall be eased. ²

3.2 Quality Control

- A. Each lot shall be qualified by the following tests are described in AITC 200-2020:
 - 1. "AITC Test T107 Shear Test."
 - 2. "AITC Test T110 Cyclic Delamination Test."
 - 3. "AITC Test T119 Full Size End Joint Tension Test."
- B. Each order shall be inspected to verify that beams comply with the shop order.

¹ This is industrial appearance grade. Additional surfacing is included with architectural and premium grade.

² This is architectural and premium grade only.